



www.gruppochemrich.com

info@gruppochemrich.com

FACTORY

🇧🇪 Heuvelstraat 44 3550
Heusden-zolder / BELGIË
☎ +32 483 22 65 39 (WhatsApp)

OFFICE

🇹🇷 Mescid Mh. Demokrasi Cd.
Birmes San.St.A 4 no:14
Tuzla/İSTANBUL
+90 216 393 70 56
+90 532 495 79 55 (WhatsApp)

RICCO AR

Acrylic polymer

PHYSICAL PROPERTIES

Physical State	: Liquid
Appearance	: Clear, colourless to pale yellow coloured viscos liquid
Chemical Structure	: Acrylic polymer solution
Ionic Structure	: Anionic
pH	: 4,00 – 7,50 (10% in water)
Dry Matter	: 30,00 – 35,00 % @ 105 °C
Viscosity	: 1700 – 4000 cPs
Solubility	: Easily soluble in warm or cold water
Film characteristic	: Medium soft and elastic

GENERAL

- **RICCO AR** is an NPEO / APEO free acrylic resin sodium salt used for retanning and filling of chrome and chrome vegetable tanned upper leather.
- **RICCO AR** is an acrylic polymer which prevents grain looseness, leads to a firm grain, has a selective filling and medium soft effect.
- **RICCO AR** shows extremely good filling performance when it is used above pH 4.2-4.5. If used at pH > 5 the resulting leather is soft and suitable for dry milled shoe upper leathers.
- **RICCO AR** is diluted with water at 40-60°C before the addition to the drum.

APPLICATION

In shoe upper leather retannage (On shaved weight %)

% 50	Water at 40 °C	
% 3	RICCO AR	20'
% 3	RICCO RS7	
% 3	RICCO RK	
% 3	RICCO NK	
% 2	Mimosa	
% X	Dyestuff	60-90'

Fatliquoring is applied as usual.

PACKAGING

60 kg PE drum.

STORAGE

Keep containers tightly closed in a dry, cool and well-ventilated area. Store between 5 – 30 °C. Shelf life is 1 year under conditions of normal use.

HEALTH – SAFETY

Refer to safety data sheet for health and safety informations.

Recommendations given in this bulletin are based on tests believed to be reliable. However, the use of the product is beyond the control of Chemrich Kimya San. ve Tic. A.Ş. and no guarantee, expressed or implied, is made as to the effects of such or the results to be obtained if not used in accordance with directions or established safe practice. The buyer must assume all responsibility, including injury or damage, resulting from misuse of the product as such, or in combination with other materials.

Şirket Ünvanı
Adres
Ülke
Telefon

CHEMRICH KİMYA SANAYİ ve TİCARET A.Ş.
Mescit Mah. Demokrasi Cad. Birmes San. Sit. A4 Blok No:3 V/14 Tuzla - İSTANBUL
Türkiye
0216 393 70 56

