



www.gruppochemrich.com

info@gruppochemrich.com

FACTORY

🇧🇪 Heuvelstraat 44 3550
Heusden-zolder / BELGIË
☎ +32 483 22 65 39 (WhatsApp)

OFFICE

🇹🇷 Mescid Mh. Demokrasi Cd.
Birmes San.St.A 4 no:14
Tuzla/İSTANBUL
+90 216 393 70 56
+90 532 495 79 55 (WhatsApp)

RICCO WWR1

TECHNICAL PROPERTIES

Appearance	: Milky white liquid
Nature	: Combination of emulsifier and synthetic oil
Ionic Character	: Anionic
Active Content	: 49,0 - 52,0 % @ 105 °C
pH (%10)	: 6,0 - 7,5

GENERAL PROPERTIES

It serves perfect emulsion stability against electrolytes and mineral retanning.

RICCO WWR1 can be used in all leather types.

When it is used in chrome tanning; positively increase the value of tear resistance.

RICCO WWR1 is used for all kinds of leathers.

RICCO WWR1 can be combined with other fatliquors.

APPLICATION

n Chrome retanning:

%	200	Water at 35 °C	
%	0,5-1	RICCO DHG	20'
%	0,2	Formic Acid	10' (pH= 3.6-3.7)
%	2	RICCO CS	
%	4	Tankrom AB	60'
%	2	Sodium Formate	

Fatliquoring :

%	50	Water at 70 °C	
%	3	RICCO ALL	
%	3	RICCO DHG	
%	4	RICCO DSW	60'
%	2	RICCO RK	
%	X	20' Formic Acid	

PACKAGING

120 Kgs drum-1.000 Kgs IBC

STORAGE

1 Year at maximum 50 C , keep product from direct sunlight and protect from freezing

HEALTH – SAFETY

Refer to safety data sheet for health and safety informations.