

# www.gruppochemrich.com

info@gruppochemrich.com

# **FACTORY**

Heuvelstraat 44 3550 Heusden-zolder / BELGIË +32 483 22 65 39 (WhatsApp)

# **OFFICE**

Mescid Mh. Demokrasi Cd. Birmes San.St.A 4 no:14 Tuzla/iSTANBUL +90 216 393 70 56 +90 532 495 79 55 (WhatsApp)



# RICCO DD

### Dicyandiamid based synthetic tannin

#### **PHYSICAL PROPERTIES**

**Physical State**: Powder

**Appearance**: Light Brown coloured powder

**Chemical Structure**: Dicyandiamid based synthetic tanen

**Ionic Structure** : Anionic

**pH** : 9,00 – 11,00 (10% in water)

**Dry Matter** : Min. 92,00 % @ 105 ºC

### **GENERAL**

- RICCO DD can be used for all kind of leathers.
- **RICCO DD** is a retaining resin with excellent selective filling properties for the loose areas in the leather, resulting in uniform closed flanks and firmness.
- RICCO DD can be used on its own or in combination with vegetable extracts on chrome tanned leathers bovine leathers to improve the firmness of the grain and ability to be buffed.
- The resulting articles show little elasticity, fine grain structure and uniform firmness throughout the area.
- RICCO DD can be also used for production of water resistant leather.

# RICCO DD



### **APPLICATION**

For cow shoe upper leathers;

# **Retanning/Dyeing:**

	%	150	Water at 30°C
--	---	-----	---------------

% 3 RICCO AC 20'

% 3 RICCO DD

% 3 RICCO ME

% 3 RICCO FS

% 2 Mimosa

% 1 RICCO NK

% X Dyestuff 30' Full section!!

Fatliquoring is applied as usual.

# **PACKAGING**

25 kg kraft bag.

### **STORAGE**

Keep containers tightly closed in a dry, cool and well-ventilated area. Shelf life is 2 years under conditions of normal use.

## **HEALTH - SAFETY**

Refer to safety data sheet for health and safety informations.