



www.gruppochemrich.com

info@gruppochemrich.com

FACTORY

🇧🇪 Heuvelstraat 44 3550
Heusden-zolder / BELGIË
☎ +32 483 22 65 39 (WhatsApp)

OFFICE

🇹🇷 Mescid Mh. Demokrasi Cd.
Birmes San.St.A 4 no:14
Tuzla/İSTANBUL
+90 216 393 70 56
+90 532 495 79 55 (WhatsApp)

RICCO SMC

Styrene Maleic Resin

PHYSICAL PROPERTIES

Physical State	: Liquid
Appearance	: Clear, yellow to red Brown coloured viscos liquid
Chemical Structure	: Styrene Maleic polymer solution
Ionic Structure	: Anionic
pH	: 8,00 – 9,50 (10% in water)
Dry Matter	: 32,00 – 38,00 % @ 105 °C
Viscosity	: 1700 – 4000 cPs
Solubility	: Easily soluble in warm or cold water
Film characteristic	: Medium soft

GENERAL

- **RICCO SMC** is an NPEO / APEO free resin used for retanning and filling of chrome and chrome vegetable tanned upper leather.
- **RICCO SMC** can be used for waterproof articles.
- **RICCO SMC** shows extremely good filling performance and fine elastic grain.
- **RICCO SMC** improves the grain tightness.

APPLICATION

In shoe upper leather retannage (On shaved weight %)

% 50	Water at 40 °C	
% 2	RICCO AC	20'
% 4	RICCO SMC	30'
% 3	RICCO DD RICCO	
% 3	ME RICCO NK	
% 3	Mimosa	
% 2		
% X	Dyestuff	60-90'

Fatliquoring is applied as usual.

PACKAGING

120 kg drum and 1000 kgs IBC

STORAGE

Keep containers tightly closed in a dry, cool and well-ventilated area. Store between 5 – 30 °C. Shelf life is 1 year under conditions of normal use.

HEALTH – SAFETY

Refer to safety data sheet for health and safety informations.

