

www.gruppochemrich.com

info@gruppochemrich.com

FACTORY

Heuvelstraat 44 3550 Heusden-zolder / BELGIË +32 483 22 65 39 (WhatsApp)

OFFICE

Mescid Mh. Demokrasi Cd. Birmes San.St.A 4 no:14 Tuzla/iSTANBUL +90 216 393 70 56 +90 532 495 79 55 (WhatsApp)



RICCO ME

Melamine resin based syntan

PHYSICAL PROPERTIES

Physical state : Powder

Appearance : White coloured powder

Chemical Structure: Melamine resin based syntan

pH : 9,00 – 11,00 (10% in water)

Dry Matter : Min. 95,00 % @ 105 ºC

GENERAL

- **RICCO ME** is a filler material used in retannage of chrome leathers. It may be easily used in all kinds of leather types.
- **RICCO ME** gives you perfect fullness especially for the bellies.
- leathers treated with **RICCO ME** are tight and full.





APPLICATION

Retannage for Cow Shoe Upper leather:

Retanning and Dyeing:

| % | 150 | Water | 30°C | |
|---|-----|-------|------|--|
| | | | | |

| % | 2 | RICCO AC | 20' |
|---|---|----------|-----|
| | | | |
| | | | |

RICCO DD % 3

3 RICCO ME

RICCO FS % 3

2 Mimosa %

2 **RICCO NK** %

90' Full section % Χ Dyestuff

Fatliquoring is applied as usual.

PACKAGING

25 kg kraft bag.

STORAGE

Keep containers tightly closed in a dry, cool and well-ventilated area. Shelf life is 2 years under conditions of normal use.

HEALTH - SAFETY

Refer to safety data sheet for health and safety informations.



